

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

psa.tape@averydennison.com email:

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBD 8393

SUPPORT: Polyester Urethane Foam

SUBSTRATE:

240130 - 0603 CERT NO .:

FORD ESH-M11P19-B OEM Rev Date: Jan 13

Adhesion Requirements, Cellular Rubber / Polyurethane Foam

Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.1 **Peel Strength** ASTM D903 **Specification Results Status** 0.44 N/mm 1.16 **Pass**

3.1.1, As Received

SECTION 3.1 **Peel Strength** ASTM D903 Specification Results **Status** 0.44 N/mm 0.92 **Pass**

3.1.2, Aged, Heat Aged, 7 days @ 88°C

Specification SPEC: 3.1 **Peel Strength** ASTM D903 Results **Status** 0.44 N/mm 1.30 **Pass**

3.1.2, Humidity, 7 days @ 37°C / 95% RH

SECTION 3.2 **Peel Strength** ASTM D903 **Specification** Results **Status**

No Delamination

3.2.1, Foam to Plastic Membrane, As Received

SECTION 3.3 **Bond Separation** ASTM D903 **Specification Results Status**

No Separation of Bond No Slip 3.3, 200 gram load, 1 hr @ RT

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

1-1-24 ISSUE DATE:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Foam Tearing

Pass

Pass

ANSI National Accreditation Board

ACCREDITED

TESTING LABORATORY