



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBD 8970 12 PT BD
SUPPORT: PET FOAM
SUBSTRATE: ABS
CERT NO.: 221213 - 0745



FORD ESH-M11P19-B
OEM Rev Date: Mar 93
Adhesion Requirements, Cellular Rubber / Polyurethane Foam
Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

Table with 5 columns: Section, Requirements, ASTM, Specification, Results, Status. Rows include Peel Strength (3.1.1, 3.1.2, 3.1.2), Peel Strength (3.2), Bond Separation (3.3), Quality (3.4), and Bacteria / Fungus Resistance (3.5).

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.