

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBD 8970 12 PT BD

SUPPORT: PET FOAM SUBSTRATE: PAINTED METAL 221213 - 0745 CERT NO .:



FORD ESH-M11P19-B

OEM Rev Date: Mar 93

Adhesion Requirements, Cellular Rubber / Polyurethane Foam

Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

Requirements

SECTION 3.1 ASTM D3330 **Specification Results Peel Strength** Status 0.44 N/mm 1.05 **Pass**

3.1.1, As Received

SECTION 3.1 **ASTM D3330 Specification** Results **Peel Strength** Status

3.1.2, Aged, Heat Aged, 7 days @ 88°C

0.44 N/mm 1.94 **Pass**

SECTION 3.1 **Peel Strength ASTM D3330** Specification Results **Status** 0.44 N/mm 1.21 **Pass**

3.1.2, Humidity, 7 days @ 37°C / 95% RH

SECTION 3,2 ASTM D3330 **Peel Strength**

Specification Results Status No Delamination 3.2, Foam to Plastic Membrane, As Received Foam Tearing **Pass**

SECTION 3.3 **Bond Separation ASTM D1000 Specification** Results Status No Slip

No Separation of Bond 3.3, 200 gram load, 1 hr @ RT

SECTION 3.4 **Specification** Results Quality **Status**

Easily Removed 3.4, Quality Readily Removable **Pass**

SECTION 3.5 **Bacteria / Fungus Resistance Specification** Results **Status**

3.5, Bacteria / Fungus Resistance **Must Pass** Not Tested NT

ISSUE DATE: 1-1-24 **CERTIFIED BY:**

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Pass