	N
--	---

SECTION 3.3

3.3, 200 gram load, 1 hr @ RT

TEST REPORT				
250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 email: psa.tape@averydennison.com URL: tapes.averydennison.com			ANSI National A A C C R E ISOR TESTING L	
TAPE REQUIREMENTS:3RequirementsSECTION 3.1Peel Strength3.1.1, As Received	ASTM D3330	Specification 0.44 N / mm	<u>Results</u> 0.73	
SECTION 3.1 Peel Strength 3.1.2, Aged, Heat Aged, 7 days @ 88°C	ASTM D3330	Specification 0.44 N / mm	<u>Results</u> 0.88	
SECTION <b>3.1</b> Peel Strength 3.1.2, Humidity, 7 days @ 37°C / 95% RH	ASTM D3330	Specification 0.44 N / mm	<u>Results</u> 0.99	
SECTION 3.2 Peel Strength 3.2, Foam to Plastic Membrane, As Received	ASTM D3330	Specification No Delamination	<u>Results</u> Foam Tearing	

ASTM D1000

Status Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Results

No Slip

SECTION 3.4 Specification Results Quality Status Easily Removed 3.4, Quality **Readily Removable** Pass SECTION 3.5 **Bacteria / Fungus Resistance** Specification Results Status 3.5, Bacteria / Fungus Resistance **Must Pass** Not Tested NT CERTIFIED BY: ISSUE DATE: 1-1-24

Specification

No Separation of Bond

Dave Nichols Jr, Automotive Lab Technician

**Bond Separation** 

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

