



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBD 8970
 SUPPORT: EPDM FOAM
 SUBSTRATE: ABS
 CERT NO.: 221213 - 0745



FORD ESH-M11P19-B
 OEM Rev Date: Dec 13
 Adhesion Requirements, Cellular Rubber / Polyurethane Foam
 Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION: 3.1 Peel Strength

3.1.1, As Received

Specification
0.44 N / mm

ASTM D3330

Results
 0.44

Status
Pass

SECTION: 3.1 Peel Strength

3.1.2, Aged, Heat Aged, 7 days @ 88°C

Specification
0.44 N / mm

Results
 1.10

Status
Pass

SPEC: 3.1 Peel Strength

3.1.2, Humidity, 7 days @ 37°C / 95% RH

Specification
0.44 N / mm

Results
 0.64

Status
Pass

SECTION: 3.2 Peel Strength

3.2.1, Foam to Plastic Membrane, As Received

Specification
No Delamination

Results
 Foam Tearing

Status
Pass

SECTION: 3.3 Bond Separation

3.3, 200 gram load, 1 hr @ RT

Specification
No Separation of Bond

Results
 No Slip

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.