

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FBD 8970** SUPPORT: **PET FOAM**

PP SUBSTRATE:

221213 - 0745 CERT NO .:



OEM Rev Date: Mar 93

Adhesion Requirements, Cellular Rubber / Polyurethane Foam

Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

Requirements

SECTION 3.1 ASTM D3330 **Specification Results Peel Strength Status** 0.44 N/mm 1.20 **Pass**

3.1.1, As Received

SECTION 3.1 **ASTM D3330 Specification** Results **Peel Strength** Status

3.1.2, Aged, Heat Aged, 7 days @ 88°C

0.44 N/mm 1.20 **Pass**

SECTION 3.1 **Peel Strength ASTM D3330** Specification Results **Status**

3.1.2, Humidity, 7 days @ 37°C / 95% RH 0.44 N/mm 1.36 **Pass**

SECTION 3,2 ASTM D3330 **Specification** Results **Peel Strength** Status No Delamination 3.2, Foam to Plastic Membrane, As Received Foam Tearing

SECTION 3.3 **Bond Separation ASTM D1000 Specification** Results Status No Separation of Bond No Slip 3.3, 200 gram load, 1 hr @ RT **Pass**

SECTION 3.4 Results **Specification** Quality **Status** Easily Removed 3.4, Quality Readily Removable **Pass**

SECTION 3.5 **Bacteria / Fungus Resistance Specification** Results **Status**

3.5, Bacteria / Fungus Resistance **Must Pass** Not Tested NT

ISSUE DATE: 1-1-24 **CERTIFIED BY:**

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

ANSI National Accreditation Board

ACCREDITED

TESTING LABORATORY

Pass