



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBD 8970
SUPPORT: PEU FOAM
SUBSTRATE: PP
CERT NO.: 221213 - 0745

FORD ESH-M11P19-B
OEM Rev Date: Mar 93
Adhesion Requirements, Cellular Rubber / Polyurethane Foam
Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.1 Peel Strength ASTM D3330 Specification 0.44 N / mm Results 0.96 Status Pass
3.1.1, As Received

SECTION 3.1 Peel Strength ASTM D3330 Specification 0.44 N / mm Results 0.96 Status Pass
3.1.2, Aged, Heat Aged, 7 days @ 88°C

SECTION 3.1 Peel Strength ASTM D3330 Specification 0.44 N / mm Results 1.19 Status Pass
3.1.2, Humidity, 7 days @ 37°C / 95% RH

SECTION 3.2 Peel Strength ASTM D3330 Specification No Delamination Results Foam Tearing Status Pass
3.2, Foam Rubber to Plastic Membrane, As Received

SECTION 3.3 Bond Separation ASTM D1000 Specification No Separation of Bond Results No Slip Status Pass
3.3, 200 gram load, 1 hr @ RT

SECTION 3.4 Quality Specification Readily Removable Results Easily Removed Status Pass
3.4, Quality

SECTION 3.5 Bacteria / Fungus Resistance Specification Must Pass Results Not Tested Status NT
3.5, Bacteria / Fungus Resistance

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.