

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

## **TEST REPORT**

 PRODUCT:
 A501A

 SUPPORT:
 2 MIL PET

 SUBSTRATE:
 PP

 CERT NO.:
 230109 - 1056

FORD ESH-M11P19-B



OEM Rev Date: Jan 13 Adhesion Requirements, Cellular Rubber / Polyurethane Foam Pressure Sensitive Film with Biocide

Tested in accordance with JDC protocols and provided as product information only. Actual product and application substrates would need to be tested for OEM certification.

TAPE REQUIREMENTS:3RequirementsSECTION 3.1Peel Strength3.1.1, As Received	ASTM D903	Specification 0.44 N / mm	<u>Results</u> 0.75	<u>Status</u> Pass
SECTION 3.1 Peel Strength	ASTM D903	Specification	<u>Results</u>	<u>Status</u>
3.1.2, Aged, Heat Aged, 7 days @ 88°C		0.44 N / mm	1.70	Pass
SPEC: <b>3.1 Peel Strength</b>	ASTM D903	Specification	<u>Results</u>	<u>Status</u>
3.1.2, Humidity, 7 days @ 37°C / 95% RH		0.44 N / mm	1.32	Pass
SECTION <b>3.2 Peel Strength</b>	ASTM D903	Specification	<u>Results</u>	<u>Status</u>
3.2.1, Foam to Plastic Membrane, As Received		No Delamination	Cohesive	Pass
SECTION 3.3 Bond Separation	ASTM D903	Specification	<u>Results</u>	<u>Status</u>
3.3, 200 gram load, 1 hr @ RT		No Separation of Bond	No Slip	Pass
CERTIFIED BY: Dave Nichols Jr, Automotive Lab	Technician	ISSUE DATE:	<u>1-1-24</u>	

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date: