



TEST REPORT

250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

PRODUCT: **A5079A**
 SUPPORT: **2 MIL PET**
 SUBSTRATE: **PP**
 CERT NO.: **230109 - 1056**



FORD ESH-M11P19-B
 OEM Rev Date: Jan 13
 Adhesion Requirements, Cellular Rubber / Polyurethane Foam
 Pressure Sensitive Film with Biocide

Tested in accordance with JDC protocols and provided as product information only. Actual product and application substrates would need to be tested for OEM certification.

TAPE REQUIREMENTS:

3 Requirements

SECTION	Requirements	ASTM	Specification	Results	Status
3.1	Peel Strength	D903			
3.1.1	As Received		0.44 N / mm	0.49	Pass
3.1.2	Aged, Heat Aged, 7 days @ 88°C		0.44 N / mm	0.52	Pass
SPEC:	Peel Strength	D903			
3.1.2	Humidity, 7 days @ 37°C / 95% RH		0.44 N / mm	0.63	Pass
3.2	Peel Strength	D903			
3.2.1	Foam to Plastic Membrane, As Received		No Delamination	Cohesive	Pass
3.3	Bond Separation	D903			
3.3	200 gram load, 1 hr @ RT		No Separation of Bond	No Slip	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.