



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8392 EZ**
 SUPPORT: **LOW PERM FOAM**
 SUBSTRATE: **SS**
 CERT NO.: **221213 - 0755**



FORD ESH-M11P40-A
 OEM Rev Date: Sep 87
 Adhesion Requirements
 Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION	Requirements	Specification	ASTM	Results	Status
SECTION 3.2	Peel Strength, Plastic Membrane to Panel 3.2.1, As Received	0.22 N / mm	ASTM D903	1.29	Pass
SECTION 3.2	Peel Strength, Plastic Membrane to Panel 3.2.2, Aged, Heat Aged, 7 days @ 88°C	0.22 N / mm	ASTM D903	1.61	Pass
SECTION 3.2	Peel Strength, Plastic Membrane to Panel 3.2.2, Humidity, 7 days @ 37°C / 95% RH	0.11 N / mm	ASTM D903	0.89	Pass
SECTION 3.3	Peel Strength 3.3.1, Foam to Plastic Membrane, As Received	No Delamination	ASTM D903	Foam Tearing	Pass
SECTION 3.4	Bond Separation 3.4, 200 gram load, 1 hr @ RT	No Separation of Bond		No Slip	Pass
SECTION 3.5	Quality 3.5, Quality	Readily Removable		Easily Removed	Pass
SECTION 3.6	Bacteria / Fungus Resistance 3.6, Bacteria / Fungus Resistance	Must Pass		NGS - No Growth on Sample	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.