



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

### TEST REPORT

PRODUCT: **FT 8392**  
SUPPORT: **LOW PERM FOAM**  
SUBSTRATE: **SS**  
CERT NO.: **221213 - 0755**



**FORD ESH-M11P40-A**  
OEM Rev Date: Sep 87  
Adhesion Requirements  
Pressure Sensitive Film with Biocide

#### TAPE REQUIREMENTS:

#### 3 Requirements

SECTION 3.2 **Peel Strength, Plastic Membrane to Panel**  
3.2.1, As Received

Specification  
**0.22 N / mm**

ASTM D903

Results  
1.29

Status  
**Pass**

SECTION 3.2 **Peel Strength, Plastic Membrane to Panel**  
3.2.2, Aged, Heat Aged, 7 days @ 88°C

Specification  
**0.22 N / mm**

ASTM D903

Results  
1.61

Status  
**Pass**

SECTION 3.2 **Peel Strength, Plastic Membrane to Panel**  
3.2.2, Humidity, 7 days @ 37°C / 95% RH

Specification  
**0.11 N / mm**

ASTM D903

Results  
0.89

Status  
**Pass**

SECTION 3.3 **Peel Strength**  
3.3.1, Foam to Plastic Membrane, As Received

Specification  
**No Delamination**

ASTM D903

Results  
Foam Tearing

Status  
**Pass**

SECTION 3.4 **Bond Separation**  
3.4, 200 gram load, 1 hr @ RT

Specification  
**No Separation of Bond**

Results  
No Slip

Status  
**Pass**

SECTION 3.5 **Quality**  
3.5, Quality

Specification  
**Readily Removable**

Results  
Easily Removed

Status  
**Pass**

SECTION 3.6 **Bacteria / Fungus Resistance**  
3.6, Bacteria / Fungus Resistance

Specification  
**Must Pass**

Results  
NGS - No Growth on Sample

Status  
**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.