



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392
SUPPORT: PEU FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221213 - 0755



FORD ESH-M11P40-A
OEM Rev Date: Sep 87
Adhesion Requirements
Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.2 Peel Strength, Plastic Membrane to Panel
3.2.1, As Received
Specification: 0.22 N / mm
ASTM D903
Results: 0.78
Status: Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel
3.2.2, Aged, Heat Aged, 7 days @ 88°C
Specification: 0.22 N / mm
ASTM D903
Results: 1.05
Status: Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel
3.2.2, Humidity, 7 days @ 37°C / 95% RH
Specification: 0.11 N / mm
ASTM D903
Results: 1.12
Status: Pass

SECTION 3.3 Peel Strength
3.3.1, Foam to Plastic Membrane, As Received
Specification: No Delamination
ASTM D903
Results: Foam Tearing
Status: Pass

SECTION 3.4 Bond Separation
3.4, 200 gram load, 1 hr @ RT
Specification: No Separation of Bond
Results: No Slip
Status: Pass

SECTION 3.5 Quality
3.5, Quality
Specification: Readily Removable
Results: Easily Removed
Status: Pass

SECTION 3.6 Bacteria / Fungus Resistance
3.6, Bacteria / Fungus Resistance
Specification: Must Pass
Results: Not Tested
Status: Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.