



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBD 8970 12 PT BD
SUPPORT: PET FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221213 - 0756

FORD ESH-M11P40-A
OEM Rev Date: Sep 87
Adhesion Requirements
Pressure Sensitive Film with Biocide

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.2 Peel Strength, Plastic Membrane to Panel
3.2.1, As Received
Specification 0.22 N / mm
ASTM D3330
Results 1.05
Status Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel
3.2.2, Aged, Heat Aged, 7 days @ 88°C
Specification 0.22 N / mm
ASTM D3330
Results 1.94
Status Pass

SECTION 3.2 Peel Strength, Plastic Membrane to Panel
3.2.2, Humidity, 7 days @ 37°C / 95% RH
Specification 0.11 N / mm
ASTM D3330
Results 1.21
Status Pass

SECTION 3.3 Peel Strength
3.3.1, Foam to Plastic Membrane, As Received
Specification No Delamination
ASTM D3330
Results Foam Tearing
Status Pass

SECTION 3.4 Bond Separation
3.4, 200 gram load, 1 hr @ RT
Specification No Separation of Bond
ASTM D1000
Results No Slip
Status Pass

SECTION 3.5 Quality
3.5, Quality
Specification Readily Removable
Results Easily Removed
Status Pass

SECTION 3.6 Bacteria / Fungus Resistance
3.6, Bacteria / Fungus Resistance
Specification Must Pass
Results Not Tested
Status Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.