

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

FORD ESH-M11P40-A

PRODUCT:

SUPPORT:

CERT NO .:

SUBSTRATE:

OEM Rev Date: Sep 87 Adhesion Requirements

Pressure Sensitive Film with Biocide



TAPE REQUIREMENTS:

Requirements

SECTION 3.2 **Specification ASTM D3330** Peel Strength, Plastic Membrane to Panel **Results** Status 5 4 1 0.22 N/mm 1.25 **Pass**

TEST REPORT

FBD 8970

PET FOAM

221213 - 0756

ABS

3.2.1, As Received

SECTION 3.2 Peel Strength, Plastic Membrane to Panel **Specification ASTM D3330** Results **Status** 0.22 N/mm 1.96 **Pass**

3.2.2, Aged, Heat Aged, 7 days @ 88°C

Specification

Specification

Must Pass

ASTM D3330

ASTM D1000

Original Test Date:

1-15-2012

Results

Not Tested

Page 1 of 1

Status

Pass

Peel Strength, Plastic Membrane to Panel SECTION 3.2

3.2.2, Humidity, 7 days @ 37°C / 95% RH 0.11 N/mm 1.49 **Pass**

SECTION 3,3 **Peel Strength**

Specification ASTM D3330 Results Status No Delamination 3.3.1, Foam to Plastic Membrane, As Received Foam Tearing **Pass**

SECTION 3.4 **Bond Separation**

Results **Status** 3.4, 200 gram load, 1 hr @ RT No Separation of Bond No Slip **Pass**

Results SECTION 3.5 **Specification** Quality **Status** Easily Removed Readily Removable **Pass**

3.5, Quality

Bacteria / Fungus Resistance SECTION 3,6 **Specification** Results **Status**

3.6, Bacteria / Fungus Resistance

CERTIFIED BY: ISSUE DATE: 1-1-24

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.