



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392 12 PT BD
SUPPORT: PEU FOAM
SUBSTRATE: PP
CERT NO.: 221209 - 1452



FORD ESH-M4D291-E
OEM Rev Date: Jul 09
Polyurethane Foam, Restricted Flow - Flexible Die Cut - with Adhesive Backing

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

SECTION 3.2 Finished Part - Adhesion Peel Strength

3.2.6, As Received, 2 hrs @ RT

Specification
0.438 N / mm

ASTM D903

Results
0.61

Status
Pass

SECTION 3.2 Finished Part - Adhesion Peel Strength

3.2.6, Oven Aged, 168 hrs @ 88°C

Specification
0.438 N / mm

Results
0.68

Status
Pass

SPEC: 3.2 Finished Part - Adhesion Peel Strength

3.2.6, RH Aged, 168 hrs @ 38°C / 95% RH

Specification
0.438 N / mm

Results
0.80

Status
Pass

SECTION 3.2 Finished Part - Adhesion Peel Strength

3.2.7, Dead Load Test, As Received, 8 hrs @ RT - 227 gram Load

Specification
No Separation

Results
No Slip

Status
Pass

SECTION 3.2 Finished Part - Adhesion Peel Strength

3.2.7, Dead Load Test, As Received, 4 hrs @ 50°C - 227 gram Load

Specification
No Separation

Results
No Slip

Status
Pass

SECTION 3.2 Finished Part - Adhesion Peel Strength

3.2.8, Release Film Separation

Specification
0.055 mm

Results
0.01

Status
Pass

CERTIFIED BY:

Signature of Jake Cowdrick
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.