

250 Chester Street Painesville. Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

888-358-4469 Fax:

psa.tape@averydennison.com email:

URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 8392 **PEU FOAM** SUPPORT:

SUBSTRATE: PP

CERT NO .: 221213 - 0807

FORD WSA-M11P19-C OEM Rev Date: Jul 93

Adhesion Requirements, Polyurethane Foam Pressure Sensitive Adhesive, High Tack



**TAPE REQUIREMENTS:** 

3 Requirements SECTION 3.4 **Peel Strength** 

3.4.1, As Received

**Specification** 0.88 N/mm

**ASTM D3330** 

Results 0.97

**Status Pass** 

SECTION 3.4 **Peel Strength** 

3.4.2, Heat Aged, 7 days @ 88°C

**Specification** 0.88 N/mm

**ASTM D3330** 

Results 1.20

**Status Pass** 

SECTION 3.4 **Peel Strength** 

3.4.2, Humidity, 7 days @ 37°C / 95% RH

**Specification** 0.88 N/mm

**ASTM D3330** 

**Results** 1.27

**Status Pass** 

SECTION 3.5 **Peel Strength** 

3.5.1, Foam to Plastic Membrane, As Received

**Specification Foam Tear** 

**ASTM D3330** 

Results Foam Tearing **Status Pass** 

SECTION 3.6 **Creep Adhesion** 

3.6, 200 gram load, 1 hr @ RT

**Specification** 6.4 mm

Results No Slip

**Status Pass** 

**CERTIFIED BY:** 

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

6-23-2003

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.