

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

888-358-4469 Fax:

email: psa.tape@averydennison.com URL:

tapes.averydennison.com

## **TEST REPORT**

FBR 8950 12 PT BD PRODUCT:

SUPPORT: **PET FOAM** 

PP SUBSTRATE:

221213 - 0807 CERT NO.:

FORD WSA-M11P19-C

OEM Rev Date: Jul 93

Adhesion Requirements, Polyurethane Foam Pressure Sensitive Adhesive, High Tack



**TAPE REQUIREMENTS:** 

Requirements

SECTION 3.4 **Peel Strength** 

3.4.1, As Received

SECTION 3.4

**Peel Strength** 

3.4.2, Heat Aged, 7 days @ 88°C

SECTION 3.4 **Peel Strength** 

3.4.2, Humidity, 7 days @ 37°C / 95% RH

SECTION 3.5 **Peel Strength** 

3.5.1, Foam to Plastic Membrane, As Received

SECTION 3.5 **Creep Adhesion** 

3.6, 200 gram load, 1 hr @ RT

ASTM D3330 **Specification** 0.88 N/mm

**Specification** 

0.88 N/mm

**Specification** 

0.88 N/mm

**Specification** 

**Specification** 

< 6.4 mm

**Foam Tear** 

**Results** 1.48

**Status Pass** 

**ASTM D3330** 

Results 1.82

Status **Pass** 

**ASTM D3330** 

Results 9.12

**Status Pass** 

**ASTM D3330** 

**Results** Foam Tearing **Status Pass** 

Results No Slip

**Status Pass** 

**CERTIFIED BY:** 

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.