



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 1126**
 SUPPORT: **EPDM FOAM**
 SUBSTRATE: **SS**
 CERT NO.: **221213 - 0808**



FORD WSB M3G102-B

OEM Rev Date:
 Standard Requirements for Production Materials
 B - Tape, Low Density PVC Foam , Pressure Sensitive, Supersoft
 Soft, Closed Cell PVC Foam Tape with One Side Adhesive
 Coated And The Other Side Protected By A Coated Release

TAPE REQUIREMENTS:

SECTION: 3.12 Pressure Sensitive Adhesion	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.12.1, Adhesion to Stainless Steel, Initial Room Temp		440 N / m	183 * Tear	Pass

SECTION: 3.12 Pressure Sensitive Adhesion	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.12.2, Adhesion to Painted Metal, Initial Room Temp		440 N / m	197 * Tear	Pass

SECTION: 3.12 Pressure Sensitive Adhesive	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.12.3, Adhesion to Stainless Steel, Heat Resistance, 30 mins @ 120°		No Adhesion Failure	Good, Stable, No lifting or Adhesion Loss	Pass

SECTION: 3.12 Pressure Sensitive Adhesive		<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.12.3, Adhesion to Stainless Steel, Cycling Resistance, 5X, Flat 16 hrs @ 38° C / 95% RH 4 hrs @ - 29° C 4 hrs @ 82° C		No Adhesion Failure	Good, Stable, No lifting or Adhesion Loss	Pass

SECTION: 3.13 Liner Release	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.12 Initial Room Temp		11 N / m	7.6	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.