



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8714
SUPPORT: EPDM FOAM
SUBSTRATE: SS
CERT NO.: 221213 - 0808



FORD WSB M3G102-B
OEM Rev Date:
Standard Requirements for Production Materials
B - Tape, Low Density PVC Foam , Pressure Sensitive, Supersoft
Soft, Closed Cell PVC Foam Tape with One Side Adhesive
Coated And The Other Side Protected By A Coated Release

TAPE REQUIREMENTS:

SECTION: 3.12 Pressure Sensitive Adhesion ASTM D1000 Specification Results Status
3.12.1, Adhesion to Stainless Steel, Initial Room Temp 440 N / m 1159.9 Pass

SECTION: 3.12 Pressure Sensitive Adhesion Specification Results Status
3.12.2, Adhesion to Painted Metal, Initial Room Temp 440 N / m 1117.9 Pass

SECTION: 3.12 Pressure Sensitive Adhesive Specification Results Status
3.12.3, Adhesion to Stainless Steel, Heat Resistance, 30 mins @ 120° No Adhesion Failure Good, Stable, No lifting or Adhesion Loss Pass

SECTION: 3.12 Pressure Sensitive Adhesive Specification Results Status
3.12.3, Adhesion to Stainless Steel, Cycling Resistance, 5X, Flat No Adhesion Failure Good, Stable, No lifting or Adhesion Loss Pass
16 hrs @ 38° C / 95% RH
4 hrs @ - 29° C
4 hrs @ 82° C

SECTION: 3.13 Liner Release ASTM D3330 Specification Results Status
3.12 Initial Room Temp 11 N / m 8.8 Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.