



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8397**
SUPPORT: **NITRILE VINYL FOAM**
SUBSTRATE: **SS**
CERT NO.: **221213 - 0809**



FORD WSB M3G212-A
OEM Rev Date: Feb 06
Tape, Low Density EPDM Foam, Pressure Sensitive, Supersoft

TAPE REQUIREMENTS:

SECTION:	ASTM	Specification	Results	Status
3.12 Pressure Sensitive Adhesion	ASTM D1000			
3.12.1, Adhesion to Stainless Steel		500 N / m	843.5	Pass
3.12.2, Adhesion to Painted Metal		500 N / m	594.9	Pass
SECTION 3.12 Adhesion to Stainless Steel		Specification	Results	Status
3.12.3, Adhesion, 30 mins @ 120°C, Inverted		No Adhesion Loss or Failure	Good, Stable, no lifting	Pass
3.12.3, Adhesion, Environmental Cycling 5x, Inverted 16 hrs @ 38°C / 95-100% RH 4 hrs @ -30C 4 hrs @ 90°C		No Adhesion Loss or Failure	Good, Stable, no lifting	Pass
SECTION: 3.14 Fogging	SAE J1756	Specification	Results	Status
3.14, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT		60 Units	99.3	Pass
SECTION 3.15 Heat Shrink Resistance		Specification	Results	Status
3.15, 21 days @ 121°C, Painted Metal - % Height Loss		< 10% All Directions Height	0%	Pass
3.15, 21 days @ 121°C, Painted Metal - % Height Loss		< 10% All Directions Width	3%	Pass
3.15, 21 days @ 121°C, Painted Metal - % Height Loss		< 10% All Directions Length	1%	Pass
SECTION: 3.16 Liner Removal	ASTM D1000	Specification	Results	Status
3.16, Liner Removal, Initial, Room Temp		2 - 11 N / m	8.8	Pass

CERTIFIED BY: 
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.