



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT B EZ**  
 SUPPORT: **RUBBER**  
 SUBSTRATE: **PAINTED METAL**  
 CERT NO.: **221213 - 0810**



**FORD WSF-M11P8-A2**  
 OEM Rev Date: Jan 92  
 Adhesion Requirements

Sponge Rubber, High Tack

**TAPE REQUIREMENTS:**

**3 Requirements**  
 SECTION **3.3 Adhesion**  
 3.3.1, As Received

ASTM D903

Specification  
**0.88 N / mm**

Results  
 1.19

Status  
**Pass**

SECTION **3.3.2 Adhesion**  
 3.3.2.1, Heat Aged, 14 days @ 88°C

ASTM D903

Specification  
**0.33 N / mm**

Results  
 0.96

Status  
**Pass**

SECTION **3.3.2 Adhesion**  
 3.3.2.1, Humidity, 14 days @ 37°C / 95% RH

ASTM D903

Specification  
**0.66 N / mm**

Results  
 1.73

Status  
**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.  
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.