



250 Cheste **> 70 Units**
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 0900X**
 SUPPORT: **FLOCK**
 SUBSTRATE: **TPO**
 CERT NO.: **221213 - 0821**



FORD WSS-M11P62-A
 OEM Rev Date: Jun 07
 Performance Requirements for Adhesives Used in Interior Applications
 Assembly Performance Parts Below the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.4 Flammability	ISO 3795 / SAE J369	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.4, Initial, Component		100 mm / min	< B 25	Pass

SECTION: 3.5 Odor	SAE J1351	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.5 Odor, 1 hr @ 65°C - Dry		2 Rating	2 - Slight, But Noticeable Odor	Pass

3.5 Odor, 1 hr @ 65°C - Wet		2 Rating	2 - Slight, But Noticeable Odor	Pass
-----------------------------	--	-----------------	---------------------------------	-------------

SECTION: 3.6 Fogging	SAE J1756	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT		> 70 Units	103.7	Pass

3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT		> 70 Units	102.5	Pass
---	--	----------------------	-------	-------------

CERTIFIED BY:



Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.