



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 0900X PET  
SUPPORT: FLOCK  
SUBSTRATE: ABS  
CERT NO.: 221213 - 0914



### FORD WSS-M11P62-A

OEM Rev Date: Jun 07

Performance Requirements for Adhesives Used in Interior Applications  
Assembly Performance Parts Below the Belt Line

#### TAPE REQUIREMENTS:

SECTION: 3.5 Odor \*

3.5, 1 hr @ 65°C, Dry

SAE J1351\*

#### Specification

2 Rating

#### Results

2 - Slight, But Noticeable Odor

#### Status

Pass

3.5, 1 hr @ 65°C, Wet

2 Rating

2 - Slight, But Noticeable Odor

Pass

SECTION: 3.4 Flammability

3.4, Flammability, Initial, Component

SAE J369

#### Specification

100 mm / min

#### Results

< B25

#### Status

Pass

SECTION: 3.6 Fogging, Oil Bath

3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

SAE J1756 06

#### Specification

70 Units

#### Results

96.1

#### Status

Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

99.2

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.