



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 1126 12 PT BD**
 SUPPORT: **FABRIC**
 SUBSTRATE: **PP**
 CERT NO.: **221213 - 0919**



FORD WSS-M11P62-A
 OEM Rev Date: Jul 05
 Performance Requirements for Adhesives Used in Interior Applications
 Assembly Performance Parts At or Above the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.5 Odor	SAE J1351*	<u>Specification</u> 2 Rating	<u>Results</u> Not Tested	<u>Status</u> NT
---------------------------------	------------	---	------------------------------	----------------------------

SECTION: 3.4 Flammability 3.4, Flammability, Initial, Component	SAE J369	<u>Specification</u> 100 mm / min	<u>Results</u> EBRZT	<u>Status</u> Pass
--	----------	---	-------------------------	------------------------------

SECTION: 3.6 Fogging, Oil Bath 3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT	SAE J1756	<u>Specification</u> 70 Units	<u>Results</u> 79.4	<u>Status</u> Pass
---	-----------	---	------------------------	------------------------------

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT		70 Units	70.0	Pass
---	--	-----------------	------	-------------

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.