



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1149X PET
SUPPORT: FLOCK
SUBSTRATE: PP
CERT NO.: 221213 - 0914



FORD WSS-M11P62-A
OEM Rev Date: Jun 07
Performance Requirements for Adhesives Used in Interior Applications
Assembly Performance Parts Below the Belt Line

TAPE REQUIREMENTS:

Table with 5 columns: SECTION, Specification, Results, Status. Rows include Odor (3.5, 1 hr @ 65°C, Dry), Odor (3.5, 1 hr @ 65°C, Wet), Flammability (3.4, Initial, Component), and Fogging (3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT).

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.

