



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8217
SUPPORT: 1 mm FELT
SUBSTRATE: PAINTED METAL
CERT NO.: 221213 - 0902

FORD WSS-M11P62-A
OEM Rev Date: Jun 07
Performance Requirements for Adhesives Used in Interior Applications
Assembly Performance Parts Below the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.5 Odor
3.15, 1 hr @ 65°C, Dry
SAE J1351*
Specification
2 Rating
Results
2 - Slight, But Noticeable Odor
Status
Pass

3.15, 1 hr @ 65°C, Wet
2 Rating
2 - Slight, But Noticeable Odor
Pass

SECTION: 3.4 Flammability
3.4, Flammability, Initial, Component
SAE J369
Specification
100 mm / min
Results
EBRZT
Status
Pass

SECTION: 3.6 Fogging, Oil Bath
3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT
SAE J1756
Specification
70 Units
Results
84.3
Status
Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT
70 Units
99.9
Pass

CERTIFIED BY: [Signature]
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.