



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392 12 PT BD
SUPPORT: RED FLOCK
SUBSTRATE: ABS
CERT NO.: 221213 - 0911



FORD WSS-M11P62-A
OEM Rev Date: Jun 07
Performance Requirements for Adhesives Used in Interior Applications

TAPE REQUIREMENTS:

SECTION: 3.4 Flammability SAE J369 Specification Results Status
3.4, Initial, Component 100 mm / min < B 50 Pass

SECTION: 3.5 Odor SAE J1351* Specification Results Status
3.5 Odor, 1 hr @ 65°C - Dry 2 Rating 2 - Slight, But Noticeable Odor Pass

3.5 Odor, 1 hr @ 65°C - Wet 2 Rating 2 - Slight, But Noticeable Odor Pass

SECTION: 3.6 Fogging SAE J1756 Specification Results Status
3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT 70 Units 98.1 Pass

3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT 70 Units 98.7 Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.