



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8395
 SUPPORT: PET FOAM
 SUBSTRATE: PP
 CERT NO.: 221213 - 0912



FORD WSS-M11P62-A
 OEM Rev Date: Jun 07
 Performance Requirements for Adhesives Used in Interior Applications
 Assembly Performance Parts Below the Belt Line

TAPE REQUIREMENTS:

SECTION: **3.5 Odor**
 3.5, 1 hr @ 65°C, Dry

SAE J1351*

Specification
2 Rating

Results
 1 - No Noticeable Odor

Status
Pass

3.5,1 hr @ 65°C, Wet

2 Rating

2 - Slight, But Noticeable Odor

Pass

SECTION: **3.4 Flammability**
 3.4, Flammability, Initial, Component

SAE J369

Specification
100 mm / min

Results
 < B50

Status
Pass

SECTION: **3.6 Fogging, Oil Bath**
 3.6, 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT

SAE J1756

Specification
70 Units

Results
 100

Status
Pass

3.6, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

70 Units

100

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.