



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

### TEST REPORT


PRODUCT: **FT A902 PET**  
 SUPPORT: **FLOCK**  
 SUBSTRATE: **PP**  
 CERT NO.: **240808 - 0511**



**FORD WSS-M11P62-A**  
 OEM Rev Date: Jun 07  
 Performance Requirements for Adhesives Used in Interior Applications  
 Assembly Performance Parts At or Above the Belt Line

#### TAPE REQUIREMENTS:

SECTION:	Specification	Results	Status
<b>3.4 Flammability</b> 3.4, Initial, Component	ISO 3795 / SAE J369 <b>100 mm / min</b>	SE	<b>Pass</b>
<b>3.5 Odor</b> 3.5 Odor, 1 hr @ 65°C - Dry	SAE J1351 <b>2 Rating</b>	Not Tested	<b>Not Tested</b>
3.5 Odor, 1 hr @ 65°C - Wet	<b>2 Rating</b>	Not Tested	<b>Not Tested</b>
<b>3.6 Fogging, Oil Bath</b> 3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 1 hr @ RT	SAE J1756 <b>70 Units</b>	64.6	<b>Fail</b>
3.6, Component - 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT	<b>70 Units</b>	85.7	<b>Pass</b>

CERTIFIED BY:   
 David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.  
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.  
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.  
 This laboratory is not accredited for the calibrations or tests marked \*.