



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBA 8960 12 PT BD
SUPPORT: PET FOAM
SUBSTRATE: PC ABS
CERT NO.: 221213 - 1016



FORD WSS-M11P68-A1
OEM Rev Date: Jan 20
Tape, Performance, Pressure Sensitive Adhesive One-Sided, Interior Scuff Plate / Floor Area

TAPE REQUIREMENTS:

3. Requirements

SECTION: 3.5 Thickness

3.5 Thickness

Table with 5 columns: Specification, Results, Status. Row 1: FLTM BO 131-03*, Reported mm, 44.87, Reported

SECTION: 3.6 Weight

3.6 Weight

Table with 5 columns: Specification, Results, Status. Row 1: FLTM BO 131-03*, Reported g / m², 5.305, Reported

SECTION: 3.7 Breaking Strength

3.7 Breaking Strength

Table with 5 columns: Specification, Results, Status. Row 1: FLTM BO 131-03*, Reported N / 10 mm, 20.16, Reported

SECTION: 3.8 Fogging

3.8 Fogging - Photometric, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Table with 5 columns: Specification, Results, Status. Row 1: FLTM BO 131-03*, 70 Units min, 96, Pass

SECTION: 3.9 Odor

3.9.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water

Table with 5 columns: Specification, Results, Status. Row 1: FLTM BO 131-03*, Rating 3 Max, Not Perceptible, 1, Pass

3.9.2 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

Table with 5 columns: Specification, Results, Status. Row 1: Rating 3 Max, Not Perceptible, 1, Pass

3.9.3 Odor, Condition 3 - 2 hrs @ 65°C

Table with 5 columns: Specification, Results, Status. Row 1: Rating 3 Max, Perceptible, Not Disturbing, 2, Pass

SECTION: 3.10 Flammability

3.2.3 Initial, Component

Table with 5 columns: Specification, Results, Status. Row 1: SAE J369*, < 100 mm / min, < B 25, Pass

SECTION: 3.11 Adhesion Strength

3.11 Original

Table with 5 columns: Specification, Results, Mode, Status. Row 1: ASTM D1000, 300 N / m, 1385.4, CSP, Pass

3.11.2 After Short Term Environment Cycling

- 5 hrs @ -30°C
30 mins @ 23°C / 50%RH
5 hrs @ 80°C
30 mins @ 23°C / 50%RH
2 hrs @ 50°C / 95%RH
30 mins @ 23°C / 50%RH
5 hrs @ -30°C
30 mins @ 23°C / 50%RH
5 hrs @ 80°C

Table with 5 columns: Specification, Results, Mode, Status. Row 1: FLTM BO 140-01 A*, 225 N / m, 1037.8, CSP, Pass

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

Table with 5 columns: Specification, Results, Mode, Status. Row 1: FLTM BO 140-01 B*, 225 N / m, 1093.8, CSP, Pass

SECTION: 3.11 Adhesion Strength

3.11 Original

Table with 5 columns: Specification, Results, Status. Row 1: No Cracking, Blistering, Adhesion Loss or Delamination, Good, Stable, No Defects or Lifting, Pass

3.11.2 After Short Term Environment Cycling

Table with 5 columns: Results, Status. Row 1: Good, Stable, No Defects or Lifting, Pass

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

Table with 5 columns: Results, Status. Row 1: Good, Stable, No Defects or Lifting, Pass

CERTIFIED BY:

Signature of Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.