



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT A902 PET
SUPPORT: FLOCK
SUBSTRATE: ABS
CERT NO.: 231128 - 0845



FORD WSS-M11P68-A1
OEM Rev Date: Jan 20
Tape, Performance, Pressure Sensitive Adhesive One-Sided, Interior Scuff Plate / Floor Area

TAPE REQUIREMENTS:

3. Requirements

SECTION: 3.5 Thickness

3.5 Thickness - Complete Product Composite

Specification	Results	Status
FLTM BO 131-03* Reported mm	0.98	Reported

SECTION: 3.6 Weight

3.6 Weight - Complete Product Composite 100 cm²

Specification	Results	Status
FLTM BO 131-03* Reported g / m ²	3.313	Reported

SECTION: 3.7 Breaking Strength, Tape

3.7 Breaking Strength, Tape

Specification	Results	Status
FLTM BO 131-03* Reported N / 10 mm	109.42	Reported

SECTION: 3.8 Fogging

3.8 Fogging - Photometric, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification	Results	Status
FLTM BO 131-03* 70 Units min	85.7	Pass

SECTION: 3.9 Odor

3.9.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water

Specification	Results	Status
FLTM BO 131-03* Rating 3 Max	Not Tested	Not Tested

3.9.2 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

Rating 3 Max	Not Tested	Not Tested
--------------	------------	------------

3.9.3 Odor, Condition 3 - 2 hrs @ 65°C

Rating 3 Max	Not Tested	Not Tested
--------------	------------	------------

SECTION: 3.10 Flammability

3.2.3 Initial, Component

Specification	Results	Status
SAE J369* < 100 mm / min	SE	Pass

SECTION: 3.11 Adhesion Strength

3.11 Original

Specification	Results	Mode	Status
ASTM D1000 300 N / m	1421.1	PT	Pass

3.11.2 After Short Term Environment Cycling

5 hrs @ -30°C
30 mins @ 23°C / 50%RH
5 hrs @ 80°C
30 mins @ 23°C / 50%RH
2 hrs @ 50°C / 95%RH
30 mins @ 23°C / 50%RH
5 hrs @ -30°C
30 mins @ 23°C / 50%RH
5 hrs @ 80°C

FLTM BO 140-01 A* 225 N / m	1576.1	TRN	Pass
--------------------------------	--------	-----	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

FLTM BO 140-01 B* 225 N / m	1396.1	SP	Pass
--------------------------------	--------	----	------

SECTION: 3.11 Adhesion Strength

3.11 Original

Specification	Results	Status
No Cracking, Blistering, Adhesion Loss or Delamination	Good, Stable, No Defects or Lifting	Pass

3.11.2 After Short Term Environment Cycling

Good, Stable, No Defects or Lifting	Good, Stable, No Defects or Lifting	Pass
-------------------------------------	-------------------------------------	------

3.11.3 After Long Term Environment Cycling, 7 days @ 80°C

Good, Stable, No Defects or Lifting	Good, Stable, No Defects or Lifting	Pass
-------------------------------------	-------------------------------------	------

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.