



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 0900X
SUPPORT: FLOCK
SUBSTRATE: ABS
CERT NO.: 231128 - 1214



FORD WSS-M15P4-I
OEM Rev Date: Jul 21
Assembly Performance, Hard Mold-in-Color Interior Components
Horizontal or Vertical Parts At or Above the Belt Line
Above the Belt

TAPE REQUIREMENTS:

SECTION: **3.6 Impact Resistance**
23°C Room Temperature Impact @ 610 mm

Specification	Results	Status
No Cracking, Breaking or Separation	Stable, No Cracks, Breaks or Lifting	Pass

SECTION: **3.10 Fogging, Method A - Photometric**
3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification	Results	Status
70 Units	80.9	Pass

SECTION: **3.11 Odor**
Odor, Condition 1 - 24 hrs @ RT, Deionized Water

Specification	Results	Status
3 Max Rating	Not Tested	Not Tested

Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

Specification	Results	Status
3 Max Rating	Not Tested	Not Tested

Odor, Condition 3 - 2 hrs @ 65°C

Specification	Results	Status
3 Max Rating	Not Tested	Not Tested

SECTION: **3.12 Flammability**
Initial, Component,

Specification	Results	Status
< 100 mm / min	< B 25	Pass

SECTION: **3.14 Determination of 90 Degree Adhesion Strength**
3.14.1 Initial Adhesive Strength

Specification	Results	Status
0.48 N / mm	0.49	Pass

3.14.2 Long Term Heat Exposure - 7 Days @ 100°C

Specification	Results	Status
75% of Original Value	0.51	Pass

3.14.3 Short Term Heat, Humidity and Cold Exposure

Specification	Results	Status
75% of Original Value	0.52	Pass

SECTION: **3.14 Determination of 90 Degree Adhesion Strength**
3.14.1 Initial Adhesive Strength

Specification	Results	Status
	No Lifting or Appearance Changes	Pass


3.14.2 Long Term Heat Exposure - 7 Days @ 100°C

Specification	Results	Status
	No Lifting or Appearance Changes	Pass

3.14.3 Short Term Heat, Humidity and Cold Exposure

Specification	Results	Status
5 hrs @ -30°C	No Lifting or Appearance Changes	Pass
30 mins @ 23°C / 50% RH	No Lifting or Appearance Changes	Pass
5 hrs @ 100°C	No Lifting or Appearance Changes	Pass
30 mins @ 23°C / 50% RH	No Lifting or Appearance Changes	Pass
2 hrs @ 50°C / 95% RH	No Lifting or Appearance Changes	Pass
30 mins @ 23°C / 50% RH	No Lifting or Appearance Changes	Pass
5 hrs @ -30°C	No Lifting or Appearance Changes	Pass
30 mins @ 23°C / 50% RH	No Lifting or Appearance Changes	Pass
5 hrs @ 100°C	No Lifting or Appearance Changes	Pass

CERTIFIED BY:



ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.