



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 0900X PET
 SUPPORT: FLOCK
 SUBSTRATE: ABS
 CERT NO.: 231128 - 1214



FORD WSS-M15P4-I
 OEM Rev Date: Jul 21
 Assembly Performance, Hard Mold-in-Color Interior Components
 Horizontal or Vertical Parts At or Above the Belt Line
 Above the Belt

TAPE REQUIREMENTS:

SECTION: **3.6 Impact Resistance**
 23°C Room Temperature Impact @ 610 mm

Specification	Results	Status
No Cracking, Breaking or Separation	Stable, No Cracks, Breaks or Lifting	Pass

SECTION: **3.10 Fogging, Method A - Photometric**
 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification	Results	Status
70 Units	74.9	Pass

SECTION: **3.11 Odor**
 Odor, Condition 1 - 24 hrs @ RT, Deionized Water

Specification	Results	Status
3 Max Rating	Not Tested	Not Tested

Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water

Specification	Results	Status
3 Max Rating	Not Tested	Not Tested

Odor, Condition 3 - 2 hrs @ 65°C

Specification	Results	Status
3 Max Rating	Not Tested	Not Tested

SECTION: **3.12 Flammability**
 Initial, Component,

Specification	Results	Status
< 100 mm / min	< B 25	Pass

SECTION: **3.14 Determination of 90 Degree Adhesion Strength**
 3.14.1 Initial Adhesive Strength

Specification	Results	Status
0.48 N / mm	0.50	Pass

3.14.2 Long Term Heat Exposure - 7 Days @ 100°C

Specification	Results	Status
75% of Original Value	0.53	Pass

3.14.3 Short Term Heat, Humidity and Cold Exposure

Specification	Results	Status
75% of Original Value	0.61	Pass

SECTION: **3.14 Determination of 90 Degree Adhesion Strength**
 3.14.1 Initial Adhesive Strength

Specification	Results	Status
	No Lifting or Appearance Changes	Pass


3.14.2 Long Term Heat Exposure - 7 Days @ 100°C

Specification	Results	Status
	No Lifting or Appearance Changes	Pass

3.14.3 Short Term Heat, Humidity and Cold Exposure
 5 hrs @ -30°C
 30 mins @ 23°C / 50% RH
 5 hrs @ 100°C
 30 mins @ 23°C / 50% RH
 2 hrs @ 50°C / 95% RH
 30 mins @ 23°C / 50% RH
 5 hrs @ -30°C
 30 mins @ 23°C / 50% RH
 5 hrs @ 100°C

Specification	Results	Status
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass
	No Lifting or Appearance Changes	Pass

CERTIFIED BY:



ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.