



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FBA 8318 GL**
SUPPORT: **PET FOAM**
SUBSTRATE: **DuPont RK8148**
CERT NO: **230530 - 1252**



FORD WSS-M3G201-A2
OEM Rev Date: Oct 18

TEST PARAMETERS:

SECTION :	3.5 Peel Adhesion	ASTM D 3330-04 10		
	Specification: 300	N / m	<u>Results</u>	<u>Status</u>
	3.5.1, Peel Adhesion, Initial, Room Temp		362.2	Pass
SECTION :	3.5 Peel Adhesion	ASTM D 3330-04 10		
	Specification: 417	N / m	<u>Results</u>	<u>Status</u>
	3.5.2, Peel Adhesion, RH, 14 days @ 38°C / 95-100%		493.6	Pass
SECTION :	3.5 Peel Adhesion	ASTM D 3330-04 10		
	Specification: 417	N / m	<u>Results</u>	<u>Status</u>
	3.5.3, Peel Adhesion, Heat Aged, 14 days @ 80°C		581.9	Pass
SECTION :	3.5 Peel Adhesion	ASTM D 3330-04 10		
	Specification: 417	N / m	<u>Results</u>	<u>Status</u>
	3.5.4, Peel Adhesion, 30 minutes @ 120°C		623.2	Pass
SECTION :	3.5 Peel Adhesion	ASTM D 3330-04 10		
	Specification: 417	N / m	<u>Results</u>	<u>Status</u>
	3.5.5, Peel Adhesion, Cycles (7X)		593.8	Pass
	3 hrs @ 80° C			
	1 hrs @ 23° C / 50% RH			
	3 hrs @ -40° C			
	1 hrs @ 23° C / 50% RH			
	16 hrs @ 38° C / 95% RH			
	16 hrs @ 38° C / 95% RH			
	4 hrs @ -40° C			
	4 hrs @ 90° C			
SECTION :	3.6 Liner Removal	ASTM D 3330-04 10		
	Specification: < 3.6	N / m	<u>Results</u>	<u>Status</u>
	3.6.1, Liner Removal, Initial		0.011	Pass
SECTION :	3.7 Flammability	ISO 3795* / SAE J369*		
	Specification: < 100	mm / min	<u>Results</u>	<u>Status</u>
	3.7.1 Burn Rate, Component, Flammability,			Pass


Dave Nichols Jr, Automotive Lab Technician

CERTIFIED BY:

RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request in full, without the written approval of the Avery Dennison Performance Tapes. All tests performed by personnel with appropriate training and professional experience. Results are certified for the calibrations or tests marked *.

ISSUE DATE: 1-1-24