



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 8306**
 SUPPORT: **PE FOAM**
 SUBSTRATE: **PP**
 CERT NO.: **221213 - 0820**



FORD WSS M3G238 - A1
 OEM Rev Date: Jan 10
 Tape, Transit Film, Removable, Interior

TAPE REQUIREMENTS:

SECTION **3.6 Adhesion After Environmental Exposure - Interior (A1)***

| | <u>Specification</u> | <u>Results</u> | <u>Status</u> |
|--|---|--|---------------|
| 3.6.1, Weathering Resistance, FLTM BO 116-01 0 | No Adhesion Discoloration or Stain | Not Tested | NT |
| 3.6.2, Heat Resistance, 7 days @ 90°C | No Adhesion Discoloration or Stain | Good, Removable, No Staining or Transfer | Pass |
| 3.6.3, Humidity Resistance, 7 days @ 38°C / 95-100% RH | No Adhesion Discoloration or Stain | Good, Removable, No Staining or Transfer | Pass |
| 3.6.4, Environmental Cycle Resistance | No Adhesion Discoloration or Stain | Good, Removable, No Staining or Transfer | Pass |
| 5 hrs @ -30C | | | |
| 30 mins @ 23°C / 50% RH | | | |
| 5 hrs @ 90°C | | | |
| 30 mins @ 23°C / 50% RH | | | |
| 2 hrs @ 50°C / 95-100% RH | | | |
| 30 mins @ 23°C / 50% RH | | | |
| 5 hrs @ -30C | | | |
| 30 mins @ 23°C / 50% RH | | | |
| 5 hrs @ 90°C | | | |

SECTION: **3.6.5 Odor***

| | <u>Specification</u> | <u>Results</u> | <u>Status</u> |
|--------------------------------|----------------------|--|---------------|
| 3.6.5, Odor, Dry - 1 hr @ 65°C | 3 Max Rating | Clearly Perceptible, But Not Disturbing, 3 | Pass |

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.