



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT A902 PET
 SUPPORT: FLOCK
 SUBSTRATE: SS
 CERT NO.: 231019 - 0622



FORD WSS-M99P48-B3
 OEM Rev Date: Feb 21

Foam Performance, Pressure Sensitive Adhesive Tape (Interior, Exterior, Underhood, Underhood)
 Interior
 At or Above the Belt Line

TAPE REQUIREMENTS:

SECTION: 3.2.1 Odor

- 3.2.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water
- 3.2.1 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water
- 3.2.1 Odor, Condition 3 - 2 hrs @ 65°C

Specification

FLTM BO 131-03

Results

Not Tested
 Not Tested
 Not Tested

Status

Not Tested
Not Tested
Not Tested

Rating 3 Max
 Rating 3 Max
 Rating 3 Max

SECTION: 3.2.2 Fogging, Photometric

- 3.2.2, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification

SAE J1756

Results

90

Status

Pass

70 Units min

SECTION: 3.2.3 Flammability

- 3.2.3 Burn Rate, Component

Specification

ISO 3795* / SAE J369*

Results

SE/NBR

Status

Pass

< 100 mm / min

SECTION 3.2.4 Resistance to Mildew

- 3.2.4 7 Days @ 38°C / 98% RH

Specification

FLTM BO 131-03*

Results

No Offensive Odor or Evidence of Mildew

Status

Pass

No Visible Mildew Growth
 or Objectionable Odor

SECTION 3.2.5 Accelerated Weathering Resistance

- 3.2.5 2250 Hours, ISO 105-A-02 AATCC Eval 1

Specification

ASTM D7869*

Results

Not Tested

Status

Not Tested

Rating 4 Min

SECTION: 3.2.6 Adhesion Strength to Steel

- 3.2.6.1 Original Bond Strength
- 3.2.6.2 After Heat Ageing Change, 168 hrs @ 100°C
- 3.2.6.3 After Environmental Cycling Change, 10 Cycles
 - 4 hrs @ 100°C
 - 4 hrs @ 38°C / 95% RH
 - 16 hrs @ -30°C

Specification

ASTM D1000

Results

1.54

Mode

PT

Status

Pass

0.48 N / mm

0.36 N / mm

- 25% max

0.36 N / mm

- 25% max

1.84

TRN

Pass

1.79

TRN

Pass

SECTION: 3.2.6 Adhesion Strength to Steel

- 3.2.6.1 Original Bond Strength
- 3.2.6.2 After Heat Ageing Change, 168 hrs @ 100°C
- 3.2.6.3 After Environmental Cycling Change, 10 Cycles

Specification

ASTM D1000

Results

Good, Stable, No Defects or Lifting

Status

Pass

No Cracking, Delamination
 or Cracking

Good, Stable, No Defects or Lifting

Pass

Good, Stable, No Defects or Lifting

Pass

SECTION 3.2.8 Stress Cracking Test for Plastics

- 3.2.8 Stress Cracking Test for Plastics

Specification

ASTM D1000

Results


Not Tested

Status

Not Tested

No Cracking or Cracking

CERTIFIED BY:



David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.