



250 Chester Street
Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 0900X
SUPPORT: FLOCK
SUBSTRATE: SS
STD CERT NO.: 231204 - 0816

GM 9985281
OEM Rev Date: Sep 15
Adhesive, Film
Table 1: Material Properties as Received
Low Temperature



Table 1: Material Properties as Received

3 Requirements

SECTION: **Mass**

Product Less Liner

Specification	Results	Status
> 0.06 < 0.20 kg/m ²	0.13	Pass

SECTION: **Solids Content**

Solids, 45 mins @ 105°C

Specification	Results	Status
94.5 % min	99.7	Pass

SECTION: **Thickness of Adhesive**

0.09 to 1.75 mm (.004 to .065 in)

TAPPI 411

Specification	Results	Status
> 0.090 < 1.650 mm	0.157	Pass

SECTION: **Peel Adhesion**

Table 1, Initial, Room Temp

ASTM D3330

Specification	Results	Status
535 N / m	896.4	Pass

SECTION: **Holding Power**

Table 1, Low Temp, 1000g @ 23°C, PET Support

ASTM D3564 Method A

Specification	Results	Status
> 25 mins	126.2	Pass

SECTION: **Liner Removal**

Table 1, Initial, Room Temp

ASTM D3330

Specification	Results	Status
< 45 N / m	13.9	Pass

CERTIFIED BY:



Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.