



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

### TEST REPORT

PRODUCT: FT 0900X PET  
SUPPORT: FLOCK  
SUBSTRATE: SS  
STD CERT NO.: 231204 - 0816



GM 9985281  
OEM Rev Date: Sep 15  
Adhesive, Film  
Table 1: Material Properties as Received  
Low Temperature

#### Table 1: Material Properties as Received

##### 3 Requirements

SECTION: **Mass**

Product Less Liner

Specification	Results	Status
> 0.06 < 0.20 kg/m <sup>2</sup>	0.07	Pass

SECTION: **Solids Content**

Solids, 45 mins @ 105°C

Specification	Results	Status
94.5 % min	99.6	Pass

SECTION: **Thickness of Adhesive**

0.09 to 1.75 mm (.004 to .065 in)

TAPPI 411

Specification	Results	Status
> 0.090 < 1.650 mm	0.104	Pass

SECTION: **Peel Adhesion**

Table 1, Initial, Room Temp

ASTM D3330

Specification	Results	Status
535 N / m	538.6	Pass

SECTION: **Holding Power**

Table 1, Low Temp, 1000g @ 23°C, PET Support

ASTM D3564 Method A

Specification	Results	Status
> 25 mins	95.0	Pass


SECTION: **Liner Removal**

Table 1, Initial, Room Temp

ASTM D3330

Specification	Results	Status
< 45 N / m	6.7	Pass

CERTIFIED BY:



Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.