



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FBA 8960**  
 SUPPORT: **PORON**  
 SUBSTRATE: **SS**  
 STD CERT NO.: **231204 - 1247**



**GM 9985281**  
 OEM Rev Date: Sep 15  
 Adhesive, Film  
 Table 1: Material Properties as Received  
 Low Temperature

**Table 1: Material Properties as Received**

**3 Requirements**

SECTION: **Mass**

Product Less Liner

<u>Specification</u>	<u>Results</u>	<u>Status</u>
<b>&gt; 0.06 &lt; 0.20 kg/m<sup>2</sup></b>	0.14	<b>Pass</b>

SECTION: **Solids Content**

Solids, 45 mins @ 105°C

<u>Specification</u>	<u>Results</u>	<u>Status</u>
<b>94.5 % min</b>	99.8	<b>Pass</b>

SECTION: **Thickness of Adhesive**

0.09 to 1.75 mm (.004 to .065 in)

TAPPI 411

<u>Specification</u>	<u>Results</u>	<u>Status</u>
<b>&gt; 0.090 &lt; 1.650 mm</b>	0.100	<b>Pass</b>

SECTION: **Peel Adhesion**

Table 1, Initial, Room Temp

ASTM D3330

<u>Specification</u>	<u>Results</u>	<u>Status</u>
<b>535 N / m</b>	646.7	<b>Pass</b>

SECTION: **Holding Power**

Table 1, Low Temp, 1000g @ 23°C, PET Support

ASTM D3564 Method A

<u>Specification</u>	<u>Results</u>	<u>Status</u>
<b>&gt; 25 mins</b>	406.4	<b>Pass</b>


SECTION: **Liner Removal**

Table 1, Initial, Room Temp

ASTM D3330

<u>Specification</u>	<u>Results</u>	<u>Status</u>
<b>&lt; 45 N / m</b>	8.5	<b>Pass</b>

CERTIFIED BY:



**Dave Nichols Jr, Automotive Lab Technician**

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.