



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392
SUPPORT: PET FOAM

SUBSTRATE: PP

CERT NO.: 221214 - 0846

GMCH MSP 200062 OEM Rev Date: Oct 17

Pressure Sensitive Adhesives - Permanent Bond Double Coated Tape - With Polyester Carrier

Permanent Bond

GENERAL REQUIREMENTS: SECTION: 3.1.3 Service Temperature Test Condition 3.1.3 Degree and 100 km (2) 4000	Specification  No Adhesion Loss or Separation	<u>Results</u> Good, Stable, No Lifting	Status
3.1.3.3 Permanent Bond: 96 hrs @ -40°C  3.1.3.3 Permanent Bond: 96 hrs @ 93°C	No Adhesion Loss or Separation	Good, Stable, No Lifting	Pass Pass
SECTION: 3.1.3 Service Temperature Test	Specification	Results	Otatus
Condition 3.1.3.3 Permanent Bond: 96 hrs @ -40°C	2 lb	5.90	Status Pass
3.1.3.3 Permanent Bond: 96 hrs @ 93°C	2 lb	7.65	Pass
SECTION: 3.1.4 Humidity Condition	Specification	Results	Status
3.1.4 50 hrs @ 38°C / 95% RH	No Adhesion Loss, Discoloration or Softening	Stable, No Lifting or Visible Change	<u>Status</u> Pass
SECTION: 3.1.5 Objectionable Odor Condition	Specification	Results	Status
3.1.5 1 hr @ 93°C	2 or Less Rating	1.3	Pass
3.1.5 1 hr @ 93°C, 1 hr @ RT	2 or Less Rating	1.0	Pass
SECTION: 3.1.7 Creep Condition 3.1.7 3.5 hrs @ 23°C under 1 lb load	Specification  No Slip	<u>Results</u> No Slip	Status Pass
GENERAL REQUIREMENTS:			
SECTION: 3.1.3 Service Temperature Test Condition	Specification	ASTM D903 / D3330  Results	Status
4.1.1.1 a) As Bonded	3.4 lb	5.07	Pass
4.1.1.1 b) 72 hrs @ 93°C	2 lb	7.79	Pass
4.1.1.1 c) 24 hrs @ -40°C	2 lb	6.32	Pass
4.1.1.1 d) 48 hrs @ 38°C / 100% RH	2 lb	6.76	Pass
4.1.1.1 e) 800 hrs @ 93°C	2 lb	3.94	Pass
SECTION: <b>4.1.1.2 Static Shear</b> <u>Condition</u> 4.1.1.2 Ambient, 6 hrs @ 23°C under 2.5 kg Load	Specification No Slip	<u>Results</u> No Slip	Status Pass
SECTION: 4.1.1.3 Suggested Adhesive Requirements Condition	<u>Specification</u>	ASTM D882  Results	<u>Status</u>
4.4.4.0) T	40 164	40.4	<b>-</b>

**CERTIFIED BY:** 

4.1.1.3 b) Elongation

4.1.1.3 a) Tensile (Breaking Factor)

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

10 lbf

60 %

Jake Cowdrick, Automotive Application Specialist

10.1

42.8

Pass Pass

ACCREDITED

TESTING LABORATORY