

888-358-4469

GENERAL REQUIREMENTS:

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT: F SUPPORT: P SUBSTRATE: A CERT NO.: 22

FT 8392 PEU FOAM ABS 221214 - 0846



GMCH MSP 200062 OEM Rev Date: Oct 17 Pressure Sensitive Adh

OEM Rev Date: Oct 17 Pressure Sensitive Adhesives - Permanent Bond Double Coated Tape - With Polyester Carrier Permanent Bond

GENERAL REQUIREMENTS: SECTION: 3.1.3 Service Temperature Test			
Condition	Specification No Adhesion Loss or Separation	<u>Results</u> Good, Stable, No Lifting	<u>Status</u>
3.1.3.3 Permanent Bond: 96 hrs @ -40°C	No Adhesion Loss of Separation	Good, Stable, No Lining	Pass
3.1.3.3 Permanent Bond: 96 hrs @ 93ºC	No Adhesion Loss or Separation	Good, Stable, No Lifting	Pass
SECTION: 3.1.3 Service Temperature Test			
Condition	Specification	Results	<u>Status</u>
3.1.3.3 Permanent Bond: 96 hrs @ -40°C	2 lb	7.07	Pass
3.1.3.3 Permanent Bond: 96 hrs @ 93°C	2 lb	9.57	Pass
SECTION: 3.1.4 Humidity			
<u>Condition</u>	Specification	Results	<u>Status</u>
3.1.4 50 hrs @ 38°C / 95% RH	No Adhesion Loss, Discoloration or Softening	Stable, No Lifting or Visible Change	Pass
SECTION: 3.1.5 Objectionable Odor			
Condition	Specification	<u>Results</u>	Status
3.1.5 1 hr @ 93⁰C	2 or Less Rating	1.3	Pass
3.1.5 1 hr @ 93°C, 1 hr @ RT	2 or Less Rating	1.0	Pass
SECTION: 3.1.7 Creep			
<u>Condition</u>	Specification	Results	<u>Status</u>
3.1.7 3.5 hrs @ 23°C under 1 lb load	No Slip	No Slip	Pass
GENERAL REQUIREMENTS:			
SECTION: 3.1.3 Service Temperature Test		ASTM D903 / D3330	
Condition	Specification 3.4 lb	<u>Results</u> 6.25	<u>Status</u>
4.1.1.1 a) As Bonded	5.4 ID	0.25	Pass
4.1.1.1 b) 72 hrs @ 93°C	2 lb	11.63	Pass
4.1.1.1 c) 24 hrs @ -40°C	2 lb	7.87	Pass
4.1.1.1 d) 48 hrs @ 38°C / 100% RH	2 lb	7.83	Pass
4.1.1.1 e) 800 hrs @ 93°C	2 lb	3.42	Pass
SECTION: 4.1.1.2 Static Shear			
Condition	Specification	Results	Status
4.1.1.2 Ambient, 6 hrs @ 23ºC under 2.5 kg Load	No Slip	No Slip	Pass
SECTION: 4.1.1.3 Suggested Adhesive Requirements for	or Handling During Assembly	ASTM D882	
Condition	Specification	Results	<u>Status</u>
4.1.1.3 a) Tensile (Breaking Factor)	10 lbf	10.1	Pass
4.1.1.3 b) Elongation	60 %	42.8	Pass
2			

CERTIFIED BY: Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date:

5-9-2018 Page 1 of 1