



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

**TEST REPORT**

SAMPLE: FT 3043  
SUPPORT: FLOCK  
SUBSTRATE: TPO  
CERT NO.: 221214 - 0903



**GMW 14444-CODE-3**  
OEM Rev Date: 0

Material Related Interior Part Performance  
CODE 3 Position Within Vehicle is Not Exposed to Direct Sunlight  
C - All Parts In Contact With Customer Feet, e.g. Floor Mat, Door Trim  
Mechanically

**TAPE REQUIREMENTS:**

SECTION: **4.3 Flammability**  
Initial, Component

GMW3232

Specification  
**< 100 mm / min**

Results  
 < B 25

Status  
**Pass**

SECTION: **4.4.6 Scratch Resistance**  
100 Cycles CS-10, 500 g Load

Specification  
**No Wear Thru to Fabric Backing**

Results  
Good, No Wear Thru

Status  
**Pass**

SECTION: **4.5.1 Odor** GMW 3205  
Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water

Specification  
**> 4 Rating**

Results  
9 Just Noticeable

Status  
**Pass**

Dry Condition, Coding B - 24 hrs @ 70°C

**> 4 Rating**

9 Just Noticeable

**Pass**

High Temp Condition - 24 hrs @ 105°C

**> 4 Rating**

8 Noticeable, Trace

**Pass**

SECTION: **4.5.1 Emission Testing** GMW 3235  
Fogging, 3 hrs @ 100°C, 21°C Cooling, Post 60 mins @ RT

Specification  
**> 60 %**

Results  
100.0

Status  
**Pass**

SECTION: **4.5.2 Impact Resistance** GMW 14093 CODE 3, Apparatus A  
After 4 hrs @ -30°C

Specification  
**No Breakage, Cracks or Separation  
from 2 - 2.5 J Impacts**

Results  
No Separation or Cracks

Status  
**Pass**

**4.5.6 Adhesive Requirements of Pressure Sensitive Adhesive, Mechanically Retained Bonded Items**

TEST: **Adhesion** GMW 14892  
As Received

Specification  
**350 N / m**

Results  
727.2

Mode  
ADHESIVE

Status  
**Pass**

Humidity - GMW 14729 Option A, 144 hrs @ 38°C / 100% RH

**350 N / m**

989.9

ADHESIVE

**Pass**

Oven Aged, 24 hrs @ 85°C, < 60s

**350 N / m**

589.5

ADHESIVE

**Pass**

Environmental Cycles 2(x), GMW 14124 Cycle M


**350 N / m**

1180.8

COHESIVE

**Cohesive-Pass**

CERTIFIED BY:

  
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.