

## 250 Chester StreetPainesville, Ohio 44077Phone:866-GO-AVERY (866-462-8379)Fax:888-358-4469email:psa.tape@averydennison.comURL:tapes.averydennison.com

TEST	REPC	RT
------	------	----

 PRODUCT:
 FT 7329X

 SUPPORT:
 2 MIL PET

 SUBSTRATE:
 ABS

 CERT NO.:
 230109 - 1103



GMW 16443-TYPE-I

OEM Rev Date: Aug 18 Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

TAPE REQUIREMENTS:3.5.1 Type I ExposureSECTION 3.3.3 Edge Adhesion

3.5.3, Initial, As Received - 24 hrs @ RT

Specification Securely Bonded

Stab

<u>Results</u> Stable, No Lifting or Removal

Stable, No Lifting or Removal

Status Pass

Pass

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option

Securely Bonded

**Securely Bonded** 

Stable, No Lifting or Removal

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Techniclan

ISSUE DATE:



Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 6-24-2021

2021 Page 1 of 1

4077

	PRODUCT:	FT 7329X
Appendix A Table A1	SUPPORT:	2 MIL PET
	SUBSTRATE:	ABS
	CERT NO.:	230109 - 1103

## Table A1: GMW16443 Type I Applications Test Data Form

Section	Test	Requirements	Sample	Visual Edge Adhesion
		1	Stable, No Lifting or Removal	
3.5.3	3.5.3 Initial, As Received - 24 hrs @ RT		2	Stable, No Lifting or Removal
			3	Stable, No Lifting or Removal
		1	Stable, No Lifting or Removal	
3.5.4	3.5.4 Heat Aged 168 hrs @ 80°C per ISO 188	Per Section 3.3	2	Stable, No Lifting or Removal
	_	3	Stable, No Lifting or Removal	
3.5.5 Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A		1	Stable, No Lifting or Removal	
		2	Stable, No Lifting or Removal	
			3	Stable, No Lifting or Removal

Section	Test	Standard	Requirements	Sample	Result
3.6 Tape Wet Out, GMW15851 -		85% Tape Wet Out	1	Not Tested	
	-		2	Not Tested	
			3	Not Tested	
			1	TBD	
	To Be Determined @ Tier		2	TBD	
			3	TBD	
3.7.2 Liner Removal	ISO 8510-2	Less Than or Equal To 65 N/m	1	Not Tested	
			2	Not Tested	
			3	Not Tested	

Aug 18

© Copyright 2017 General Motors Company All Rights Reserved