



TEST REPORT



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8327
SUPPORT: EVA FOAM
SUBSTRATE: PP
CERT NO.: 221215 - 1135

GMW 16443 TYPE-I
OEM Rev Date: Dec 10
Adhesion Performance Requirements For Adhesive Backed Foam
Type I - An adhesive backed foam composite that is entrapped and/or
mechanically retained for the life of the vehicle

Handwritten signature of Dave Nichols Jr.

Dave Nichols Jr, Automotive Lab Technician
Specification

Securely Bonded

Results

Stable, No Lifting or Removal

Status

Pass

TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION 3.3 Edge Adhesion

3.3, Initial, As Received

3.5.4, Heat Aged, ISO 188, 168 hrs @ 80C

Securely Bonded

Stable, No Lifting or Removal

Pass

3.5.5, GMW 14729 Humidity, Option B - 168 hrs @ 40C / 100% RH

Securely Bonded

Stable, No Lifting or Removal

Pass

CERTIFIED BY:

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.