



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8327
SUPPORT: PVC FOAM
SUBSTRATE: PP
CERT NO.: 221215 - 1136



GMW 16443 TYPE-I
OEM Rev Date: Dec 10
Adhesion Performance Requirements For Adhesive Backed Foam
Type I - An adhesive backed foam composite that is entrapped and/or
mechanically retained for the life of the vehicle

TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION 3.3 Edge Adhesion

3.3, Initial, As Received

Table with 3 columns: Specification, Results, Status. Row 1: Securely Bonded, Stable, No Lifting or Removal, Pass

3.5.4, Heat Aged, ISO 188, 168 hrs @ 80C

Table with 3 columns: Specification, Results, Status. Row 1: Securely Bonded, Stable, No Lifting or Removal, Pass

3.5.5, GMW 14729 Option B, 168 hrs @ 40°C / 100% RH

Table with 3 columns: Specification, Results, Status. Row 1: Securely Bonded, Stable, No Lifting or Removal, Pass

CERTIFIED BY: [Signature]
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.