



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBD 8970
SUPPORT: LOW PERM FOAM
SUBSTRATE: ABS
STD CERT NO.: 221215 - 1159



GMW 16443 TYPE-I
OEM Rev Date: Dec 10
Adhesion Performance Requirements For Adhesive Backed Foam
TYPE I - An adhesive backed foam composite that is entrapped
and/or mechanically retained for the life of the vehicle
GMW 3221 Code A - 50% RH (+/- 5%)

TAPE REQUIREMENTS:

3.5.1 TYPE I Exposure

SECTION 3.3 Edge Adhesion

3.53, Initial, As Received

Table with 3 columns: Specification (Securely Bonded), Results (Stable, No Lifting or Removal), Status (Pass)

3.54, Heat Aged, ISO 188 07, 168 hrs @ 80C

Table with 3 columns: Specification (Securely Bonded), Results (Stable, No Lifting or Removal), Status (Pass)

3.55, Humidity, GMW 14729 10 Option A, 168 hrs @ 38°C / 100% R

Table with 3 columns: Specification (Securely Bonded), Results (Stable, No Lifting or Removal), Status (Pass)

CERTIFIED BY:

Signature of Dave Nichols Jr.
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.