

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **SA 1123** SUPPORT: 2 MIL PET

SUBSTRATE: PP

CERT NO.: 241016 - 0730



GMW 16443-TYPE-I OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam

Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION 3.3.3 Edge Adhesion 3.5.3, Initial, As Received - 24 hrs @ RT

Specification

Results

Status Pass

Securely Bonded

Stable, No Lifting or Removal

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188,

Securely Bonded

Stable, No Lifting or Removal

Pass

3.5.5, Humidity 168 hrs @ $38^{\rm o}{\rm C}$ / 100% RH per GMW 14729 Option

Securely Bonded

Stable, No Lifting or Removal

Pass

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE: <u>1-1-24</u>

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked * .

PRODUCT: SA 1123

SUPPORT: 2 MIL PET

Appendix A Table A1

SUBSTRATE: PP

CERT NO.: 241016 - 0730

Table A1: GMW16443 Type I Applications Test Data Form

| Section | Test | Requirements | Sample | Visual Edge Adhesion |
|---------|---|-----------------|--------|-------------------------------|
| 3.5.3 | Initial, As Received - 24 hrs @ RT | Per Section 3.3 | 1 | Stable, No Lifting or Removal |
| | | | 2 | Stable, No Lifting or Removal |
| | | | 3 | Stable, No Lifting or Removal |
| 3.5.4 | Heat Aged 168 hrs @ 80°C per ISO 188, | | 1 | Stable, No Lifting or Removal |
| | | | 2 | Stable, No Lifting or Removal |
| | | | 3 | Stable, No Lifting or Removal |
| 3.5.5 | Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option B | | 1 | Stable, No Lifting or Removal |
| | | | 2 | Stable, No Lifting or Removal |
| | | | 3 | Stable, No Lifting or Removal |

| Section | Test | Standard | Requirements | Sample | Result |
|---------|---------------------------|-------------------------|----------------------------------|--------|--------|
| 3.6 | Tape Wet Out, GMW15851 | - | 85% Tape Wet Out | 1 | |
| | | | | 2 | |
| | | | | 3 | |
| | Release Liner Contact | To Be Determined @ Tier | No Lift Prior To Vehicle Install | 1 | TBD |
| | | | | 2 | TBD |
| | | | | 3 | TBD |
| | Liner Removal | ISO 8510-2 | Less Than or Equal To 65 N/m | 1 | |
| | | | | 2 | |
| | | | | 3 | |