



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 1123  
SUPPORT: 5 MIL BLACK UHMWPE  
SUBSTRATE: ABS  
CERT NO.: 221215 - 1429



**GMW 16443-TYPE-II-EXTERIOR-CYCLE-C**

OEM Rev Date: Aug 18  
Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam  
Type II - An adhesive backed foam composite that is retained by the adhesive for the life of the vehicle

Passing Type II Meets and Exceeds 3.5.1 Type I Exposure Requirements

**TAPE REQUIREMENTS:**

**3.5.2 TYPE-II Exposure**

**SECTION 3.3.3 Edge Adhesion**

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -30°C
- 72 hrs @ 70°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ -30°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ 70°C
- 24 hrs @ 38°C / 100% RH

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

**SECTION 3.4 Peel Adhesion**

ISO 8510-2

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -30°C
- 72 hrs @ 70°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ -30°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ 70°C

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

**SECTION 3.5.8 Cold Shock**

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

**SECTION: 3.7.1 Release Liner**

3.7.2, Liner Removal @ RT

	<u>Specification</u>	<u>Results</u>	<u>Mode</u>	<u>Status</u>
3.5.3, Initial, As Received - 24 hrs @ RT	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.3, Initial, As Received - 24 hrs @ RT	525 N / m	1131.3	CF	Pass
3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188	525 N / m	991.8	CF	Pass
3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A	525 N / m	1085.8	CF	Pass
3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C	525 N / m	903.7	CF	Pass
3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	525 N / m	1130.7	CF	Pass
3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	No Separation from 2	No Impact Separation		Pass
3.7.2, Liner Removal @ RT	< 65 N / m	23.9		Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

Appendix A Table A2

PRODUCT: FT 1123  
 SUPPORT: 5 MIL BLACK UHMWPE  
 SUBSTRATE: ABS  
 CERT NO.: 221215 - 1429

Table A2: GMW16443 Type II Applications Test Data Form

Section	Test	Standard	Requirements	Sample	Visual Edge Adhesion	Peel N/m	Failure Mode
3.5.3	Initial, As Received - 24 hrs @ RT	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	1161.1	CF
				2	Stable, No Lifting or Removal	1157.6	CF
				3	Stable, No Lifting or Removal	1075.3	CF
3.5.4	Heat Aged 168 hrs @ 80°C per ISO 188			1	Stable, No Lifting or Removal	1066.5	CF
				2	Stable, No Lifting or Removal	1014.0	CF
				3	Stable, No Lifting or Removal	894.9	CF
3.5.5	Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A			1	Stable, No Lifting or Removal	1047.3	CF
				2	Stable, No Lifting or Removal	1103.3	CF
				3	Stable, No Lifting or Removal	1106.8	CF
3.5.6	Cycle Exposure, GMW 14124, 2x Cycle C			1	Stable, No Lifting or Removal	972.0	CF
				2	Stable, No Lifting or Removal	893.1	CF
				3	Stable, No Lifting or Removal	845.9	CF
				1			
				2			
				3			
3.5.8	Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	1	Stable, No Lifting or Removal	1108.6	CF		
		2	Stable, No Lifting or Removal	1166.3	CF		
		3	Stable, No Lifting or Removal	1117.3	CF		

Section	Test	Standard	Requirements	Sample	Result
3.6	Tape Wet Out, GMW15851	GMW 15851 is restricted and we cannot purchase	85% Tape Wet Out	1	Not Tested
				2	Not Tested
				3	Not Tested
3.7.1	Release Liner Contact	To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
				2	TBD
				3	TBD
3.7.2	Liner Removal	ISO 8510-2	Less Than Or Equal To 65 N/m	1	24.5
				2	24.5
				3	22.8