



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8217
 SUPPORT: 2 MIL PET
 SUBSTRATE: METAL
 CERT NO.: 230109 - 1109



GMW 16443-TYPE-II-EXTERIOR-CYCLE-C

OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam
 Type II - An adhesive backed foam composite that is retained by the adhesive for the life of the vehicle

Passing Type II Meets and Exceeds 3.5.1 Type I Exposure Requirements

TAPE REQUIREMENTS:

3.5.2 TYPE-II Exposure

SECTION 3.3.3 Edge Adhesion

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -40°C*
- 72 hrs @ 80°C*
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ -40°C*
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ 80°C*
- 24 hrs @ 38°C / 100% RH

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -40°C*

<u>Specification</u>	<u>Results</u>	<u>Status</u>
Securely Bonded	Stable, No Lifting or Removal	Pass
Securely Bonded	Stable, No Lifting or Removal	Pass
	Stable, No Lifting or Removal	Pass

SECTION 3.4 Peel Adhesion

ISO 8510-2

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -40°C*
- 72 hrs @ 80°C*
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ -40°C*
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ 80°C*

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -40°C*

<u>Specification</u>	<u>Results</u>	<u>Mode</u>	<u>Status</u>
525 N / m	1370.1	CF	Pass
525 N / m	1317.5	CF	Pass
525 N / m	1204.9	CF	Pass
525 N / m	1244.6	CF	Pass

* 10°C temperature deviation per GM

SECTION 3.5.8 Cold Shock

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -40°C*

<u>Specification</u>	<u>Results</u>	<u>Status</u>
No Separation from 2	No Impact Separation	Pass

SECTION: 3.7.1 Release Liner

3.7.2, Liner Removal @ RT

<u>Specification</u>	<u>Results</u>	<u>Status</u>
< 65 N / m	16.3	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Appendix A Table A2

PRODUCT: FT 8217
 SUPPORT: 2 MIL PET
 SUBSTRATE: METAL
 CERT NO.: 230109 - 1109

Table A2: GMW16443 Type II Applications Test Data Form

Section	Test	Standard	Requirements	Sample	Visual Edge Adhesion	Peel N/m	Failure Mode
3.5.3	Initial, As Received - 24 hrs @ RT	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	1409.8	CF
				2	Stable, No Lifting or Removal	1334.5	CF
				3	Stable, No Lifting or Removal	1366.0	CF
3.5.4	Heat Aged 168 hrs @ 80°C per ISO 188			1	Stable, No Lifting or Removal	1313.5	CF
				2	Stable, No Lifting or Removal	1276.7	CF
				3	Stable, No Lifting or Removal	1362.5	CF
3.5.5	Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A			1	Stable, No Lifting or Removal	1169.8	CF
				2	Stable, No Lifting or Removal	1274.9	CF
				3	Stable, No Lifting or Removal	1169.8	CF
3.5.6	Cycle Exposure, GMW 14124, 2x Cycle C			1		1269.7	CF
				2		1164.6	CF
				3		1299.4	CF
3.5.8	Cold Shock, 72 hrs @ 54°C, 4 hrs @ -40°C*	1	Stable, No Lifting or Removal	1243.4	CF		
		2	Stable, No Lifting or Removal	1171.6	CF		
		3	Stable, No Lifting or Removal	1185.6	CF		

Section	Test	Standard	Requirements	Sample	Result
3.6	Tape Wet Out, GMW15851	GMW 15851 is restricted and we cannot purchase	85% Tape Wet Out	1	Not Tested
				2	Not Tested
				3	Not Tested
3.7.1	Release Liner Contact	To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
				2	TBD
				3	TBD
3.7.2	Liner Removal	ISO 8510-2	Less Than or Equal To 65 N/m	1	21.0
				2	15.8
				3	12.3