



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392 12 PT BD
SUPPORT: PVC FOAM
SUBSTRATE: TPO
CERT NO.: 221215 - 1447



GMW 16443-TYPE-II-EXTERIOR-CYCLE-C

OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam
Type II - An adhesive backed foam composite that is retained by the adhesive for the life of the vehicle

Passing Type II Meets and Exceeds 3.5.1 Type I Exposure Requirements

TAPE REQUIREMENTS:

3.5.2 TYPE-II Exposure

SECTION 3.3.3 Edge Adhesion

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -30°C
- 72 hrs @ 70°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ -30°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ 70°C
- 24 hrs @ 38°C / 100% RH

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

SECTION 3.4 Peel Adhesion

ISO 8510-2

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

- 17 hrs @ -30°C
- 72 hrs @ 70°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ -30°C
- 24 hrs @ 38°C / 100% RH
- 7 hrs @ 70°C

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

SECTION 3.5.8 Cold Shock

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

SECTION: 3.7.1 Release Liner

3.7.2, Liner Removal @ RT

	<u>Specification</u>	<u>Results</u>	<u>Mode</u>	<u>Status</u>
3.5.3, Initial, As Received - 24 hrs @ RT	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	Securely Bonded	Stable, No Lifting or Removal		Pass
3.5.3, Initial, As Received - 24 hrs @ RT	525 N / m	840.0	AF-P	Pass
3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188	525 N / m	1174.5	AF-P	Pass
3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A	525 N / m	1412.7	AF-P	Pass
3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C	525 N / m	1361.3	AF-P	Pass
3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	525 N / m	1590.2	AF-P	Pass
3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	No Separation from 2	No Impact Separation		Pass
3.7.2, Liner Removal @ RT	< 65 N / m	14.6		Pass

CERTIFIED BY:
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.

Appendix A Table A2

PRODUCT: FT 8392 12 PT BD
 SUPPORT: PVC FOAM
 SUBSTRATE: TPO
 CERT NO.: 221215 - 1447

Table A2: GMW16443 Type II Applications Test Data Form

Section	Test	Standard	Requirements	Sample	Visual Edge Adhesion	Peel N/m	Failure Mode
3.5.3	Initial, As Received - 24 hrs @ RT	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	877.4	AF-P
				2	Stable, No Lifting or Removal	833.6	AF-P
				3	Stable, No Lifting or Removal	809.1	AF-P
3.5.4	Heat Aged 168 hrs @ 80°C per ISO 188			1	Stable, No Lifting or Removal	1197.9	AF-P
				2	Stable, No Lifting or Removal	1145.3	AF-P
				3	Stable, No Lifting or Removal	1180.4	AF-P
3.5.5	Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A			1	Stable, No Lifting or Removal	1490.3	AF-P
				2	Stable, No Lifting or Removal	1451.8	AF-P
				3	Stable, No Lifting or Removal	1295.9	AF-P
3.5.6	Cycle Exposure, GMW 14124, 2x Cycle C			1	Stable, No Lifting or Removal	1299.4	AF-P
				2	Stable, No Lifting or Removal	1376.5	AF-P
				3	Stable, No Lifting or Removal	1408.0	AF-P
3.5.8	Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	1	Stable, No Lifting or Removal	1576.1	AF-P		
		2	Stable, No Lifting or Removal	1628.7	AF-P		
		3	Stable, No Lifting or Removal	1565.6	AF-P		

Section	Test	Standard	Requirements	Sample	Result
3.6	Tape Wet Out, GMW15851	GMW 15851 is restricted and we cannot purchase	85% Tape Wet Out	1	Not Tested
				2	Not Tested
				3	Not Tested
3.7.1	Release Liner Contact	To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
				2	TBD
				3	TBD
3.7.2	Liner Removal	ISO 8510-2	Less Than Or Equal To 65 N/m	1	10.5
				2	19.3
				3	14.0